



US008395167B2

(12) **United States Patent**
Kang et al.

(10) **Patent No.:** **US 8,395,167 B2**
(45) **Date of Patent:** **Mar. 12, 2013**

(54) **EXTERNAL LIGHT EFFICIENCY OF LIGHT EMITTING DIODES**

(75) Inventors: **Xuejun Kang**, Singapore (SG); **Zhen Chen**, Singapore (SG); **Tien Khee Ng**, Singapore (SG); **Jenny Lam**, Singapore (SG); **Shu Yuan**, Singapore (SG)

(73) Assignee: **Tinggi Technologies Private Limited**, Singapore (SG)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 545 days.

(21) Appl. No.: **12/377,380**

(22) PCT Filed: **Aug. 16, 2007**

(86) PCT No.: **PCT/SG2007/000261**

§ 371 (c)(1),
(2), (4) Date: **Jul. 14, 2010**

(87) PCT Pub. No.: **WO2008/020819**

PCT Pub. Date: **Feb. 21, 2008**

(65) **Prior Publication Data**

US 2010/0295014 A1 Nov. 25, 2010

(30) **Foreign Application Priority Data**

Aug. 16, 2006 (SG) 200605500-8

(51) **Int. Cl.**
H01L 33/00 (2010.01)

(52) **U.S. Cl.** **257/95**

(58) **Field of Classification Search** **257/95**
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

3,897,627 A	8/1975	Klatskin
4,107,720 A	8/1978	Pucel et al.
5,192,987 A	3/1993	Khan et al.
5,405,804 A	4/1995	Yabe
5,654,228 A	8/1997	Shieh et al.
5,719,433 A	2/1998	Delage et al.
5,811,927 A	9/1998	Anderson et al.
5,879,862 A	3/1999	Roh
5,917,202 A	6/1999	Haitz et al.
5,948,281 A *	9/1999	Okazaki et al. 216/26

(Continued)

FOREIGN PATENT DOCUMENTS

CN	1373522 A	10/2002
EP	1 061 590 A1	12/2000

(Continued)

OTHER PUBLICATIONS

Wada, O. "Ion-Beam etching of InP and its application to the fabrication of High Radiance InGaAsP/InP Light Emitting Diodes" J. Electrochem. Soc. 131, pp. 2373-2380 (1983).*

(Continued)

Primary Examiner — N Drew Richards


Assistant Examiner — Grant Withers

(74) *Attorney, Agent, or Firm* — Blakely, Sokoloff, Taylor & Zafman LLP

(57) **ABSTRACT**

A method to improve the external light efficiency of light emitting diodes, the method comprising etching an external surface of an n-type layer of the light emitting diode to form surface texturing, the surface texturing reducing internal light reflection to increase light output. A corresponding light emitting diode is also disclosed.

19 Claims, 5 Drawing Sheets



U.S. PATENT DOCUMENTS

6,020,261	A	2/2000	Weisman	
6,091,085	A	7/2000	Lester	
6,117,784	A	9/2000	Uzoh	
6,169,297	B1	1/2001	Jang et al.	
6,210,479	B1	4/2001	Bojarczuk et al.	
6,259,156	B1	7/2001	Kohno et al.	
6,303,405	B1	10/2001	Yoshida et al.	
6,307,218	B1	10/2001	Steigerwald et al.	
6,319,778	B1	11/2001	Chen et al.	
6,365,429	B1	4/2002	Kneissl et al.	
6,380,564	B1	4/2002	Chen et al.	
6,420,242	B1	7/2002	Cheung et al.	
6,420,732	B1	7/2002	Kung et al.	
6,420,735	B2*	7/2002	Kim	257/95
6,426,512	B1	7/2002	Ito et al.	
6,448,102	B1	9/2002	Kneissl et al.	
6,455,870	B1	9/2002	Wang et al.	
6,492,661	B1*	12/2002	Chien et al.	257/98
6,495,862	B1*	12/2002	Okazaki et al.	257/103
6,509,270	B1	1/2003	Held	
6,562,648	B1	5/2003	Wong et al.	
6,573,537	B1*	6/2003	Steigerwald et al.	257/103
6,586,875	B1	7/2003	Chen et al.	
6,589,857	B2	7/2003	Ogawa et al.	
6,627,921	B2	9/2003	Wong et al.	
6,627,989	B2	9/2003	Kohno et al.	
6,649,437	B1	11/2003	Yang et al.	
6,677,173	B2	1/2004	Ota	
6,784,460	B2*	8/2004	Ng et al.	257/95
6,791,117	B2*	9/2004	Yoshitake et al.	257/94
6,821,804	B2*	11/2004	Thibeault et al.	438/29
6,927,423	B2*	8/2005	Sawaki et al.	257/95
7,166,861	B2	1/2007	Saito et al.	
7,250,320	B2*	7/2007	Okuyama et al.	438/47
7,338,822	B2	3/2008	Wu et al.	
7,339,197	B2*	3/2008	Lin et al.	257/95
7,348,212	B2	3/2008	Schiaffino et al.	
7,525,126	B2*	4/2009	Leatherdale et al.	257/98
7,547,578	B2	6/2009	Agarwal et al.	
7,683,386	B2*	3/2010	Tanaka et al.	257/88
7,763,477	B2*	7/2010	Yuan et al.	438/22
7,781,790	B2*	8/2010	Minato et al.	257/98
7,804,101	B2*	9/2010	Niki et al.	257/98
7,943,944	B2*	5/2011	Eisert et al.	257/98
7,952,109	B2*	5/2011	Ng	257/94
7,952,110	B2*	5/2011	Haase	257/98
8,004,001	B2	8/2011	Yuan et al.	
8,034,643	B2	10/2011	Kang et al.	
8,067,269	B2	11/2011	Yuan et al.	
8,124,994	B2	2/2012	Yuan et al.	
2001/0055324	A1	12/2001	Ota	
2002/0022286	A1*	2/2002	Nikolaev et al.	438/46
2002/0034835	A1	3/2002	Chen et al.	
2002/0093023	A1	7/2002	Camras et al.	
2002/0113279	A1	8/2002	Hanamaki et al.	
2002/0117681	A1	8/2002	Weeks et al.	
2002/0134985	A1	9/2002	Chen et al.	
2002/0137243	A1	9/2002	Chen et al.	
2002/0179910	A1	12/2002	Slater, Jr.	
2003/0038284	A1	2/2003	Kurahashi et al.	
2003/0062530	A1*	4/2003	Okazaki et al.	257/79
2003/0064535	A1	4/2003	Kub et al.	
2003/0111667	A1	6/2003	Schubert	
2003/0151357	A1	8/2003	Uemura	
2003/0178626	A1*	9/2003	Sugiyama et al.	257/79
2003/0189212	A1	10/2003	Yoo	
2003/0189215	A1	10/2003	Lee et al.	
2003/0218179	A1*	11/2003	Koide et al.	257/95
2004/0026709	A1	2/2004	Bader et al.	
2004/0031967	A1	2/2004	Fudeta et al.	
2004/0033638	A1	2/2004	Bader et al.	
2004/0065889	A1	4/2004	Ueda et al.	
2004/0104395	A1	6/2004	Hagimoto et al.	
2004/0110395	A1	6/2004	Ueda et al.	
2004/0130037	A1	7/2004	Mishra et al.	
2004/0144991	A1	7/2004	Kikkawa	
2004/0164312	A1*	8/2004	Biwa et al.	257/99
2004/0171183	A1*	9/2004	Kang et al.	438/29
2004/0217362	A1	11/2004	Slater, Jr. et al.	
2004/0235210	A1	11/2004	Tamura et al.	
2005/0014303	A1*	1/2005	Tsai et al.	438/29
2005/0026399	A1	2/2005	Chien et al.	
2005/0035354	A1	2/2005	Lin et al.	
2005/0082555	A1	4/2005	Chien et al.	
2005/0087884	A1	4/2005	Stokes et al.	
2005/0093002	A1	5/2005	Tsai et al.	
2005/0098792	A1	5/2005	Lee et al.	
2005/0127397	A1	6/2005	Borges et al.	
2005/0142875	A1	6/2005	Yoo	
2005/0145865	A1*	7/2005	Okuyama et al.	257/98
2005/0164482	A1	7/2005	Saxler	
2005/0173692	A1	8/2005	Park et al.	
2005/0208435	A1	9/2005	Chen et al.	
2006/0002442	A1	1/2006	Haberern et al.	
2006/0006554	A1*	1/2006	Yoo et al.	257/900
2006/0099730	A1	5/2006	Lee et al.	
2006/0124939	A1*	6/2006	Lee et al.	257/79
2006/0151801	A1	7/2006	Doan et al.	
2006/0154389	A1	7/2006	Doan	
2006/0154390	A1	7/2006	Tran et al.	
2006/0154391	A1	7/2006	Tran et al.	
2006/0154392	A1	7/2006	Tran et al.	
2006/0154393	A1	7/2006	Doan et al.	
2006/0157721	A1	7/2006	Tran et al.	
2006/0163586	A1*	7/2006	Denbaars et al.	257/79
2006/0186418	A1	8/2006	Edmond et al.	
2007/0029541	A1*	2/2007	Xin et al.	257/14
2007/0085098	A1*	4/2007	Erchak et al.	257/95
2007/0187704	A1*	8/2007	Okuyama et al.	257/95
2008/0105303	A1	5/2008	Oswald et al.	
2008/0121908	A1	5/2008	Yuan et al.	
2008/0164480	A1	7/2008	Kang et al.	
2008/0210970	A1	9/2008	Kang et al.	
2008/0265366	A1	10/2008	Guo et al.	
2009/0068775	A1*	3/2009	Chang et al.	438/29
2009/0078954	A1*	3/2009	Shim et al.	257/98
2009/0127440	A1*	5/2009	Nakai	250/227.2
2009/0267096	A1*	10/2009	Kim	257/98
2010/0047996	A1	2/2010	Yuan et al.	
2012/0001292	A1*	1/2012	Sasaki	257/443

FOREIGN PATENT DOCUMENTS

EP	1 139 409	A2	10/2001
EP	1 326 290	A2	7/2003
EP	1 502 284	A2	2/2005
EP	1 693 891	A2	8/2006
JP	50-074876		6/1975
JP	52-055480		5/1977
JP	59-112667		6/1984
JP	63-095661		4/1988
JP	04-078186		3/1992
JP	05-291621		11/1993
JP	07-326628		12/1995
JP	10-117016		5/1998
JP	2000-164928		6/2000
JP	2000-183400		6/2000
JP	2000-277804		10/2000
JP	2000-294837		10/2000
JP	2001-035974		2/2001
JP	2001-036129		2/2001
JP	2001-049491		2/2001
JP	2001-168094		6/2001
JP	2001-168387		6/2001
JP	2001-237461		8/2001
JP	2001-274507		10/2001
JP	2001-313422		11/2001
JP	2003-152138		5/2003
JP	2003-218383		7/2003
JP	2003-303743		10/2003
JP	2003-309286		10/2003
JP	2003-318443		11/2003
JP	2003-347590		12/2003
JP	2004-072052		3/2004
JP	2004-088083		3/2004
JP	2004-319552		11/2004
JP	2005-012188		1/2005
JP	2005-236048		9/2005

JP	2005-260255	9/2005
JP	2005-286187	10/2005
JP	2006-253647	9/2006
KR	20010088931	9/2001
KR	10-0338180	5/2002
KR	10-2002-079659	10/2002
KR	20040058479	7/2004
KR	20040104232	12/2004
SG	200401424-7	3/2004
SG	200401964-2	4/2004
SG	200506301-1	9/2005
SG	200506897-8	10/2005
SG	200508210-2	12/2005
SG	200606050-3	9/2006
TW	419836 B	1/2001
TW	475276 B	2/2002
TW	540171 B	7/2003
WO	WO 01/47039 A1	6/2001
WO	WO 03/088320 A2	10/2003
WO	WO 2004/102686 A1	11/2004
WO	WO 2005/029572 A1	3/2005
WO	WO 2005/029573 A1	3/2005
WO	WO 2005/062745 A2	7/2005
WO	WO 2005/064666 A1	7/2005
WO	WO 2005/088743 A1	9/2005
WO	WO 2005/096365 A1	10/2005
WO	WO 2005/098974 A1	10/2005
WO	WO 2005/104780 A2	11/2005
WO	WO 2007/046773 A1	4/2007
WO	WO 2007/037762 A1	5/2007
WO	WO 2007/073354 A1	6/2007
WO	WO 2008/030188 A1	3/2008

OTHER PUBLICATIONS

M.K. Kelly, et al., "Optical Process for Liftoff of Group III-Nitride Films," *Physica Status Solidi (a)*, vol. 159, Issue 1, pp. R3-R4, (Nov. 28, 1996).

Tetsuzo Ueda, et al., "Vertical InGa_N-Based Blue Light Emitting Diode with Plated Metal Base Fabricated using Laser Lift-Off Technique," *Physica Status Solidi (c)*, vol. 0, Issue 7, pp. 2219-2222, (Oct. 20, 2003).

Chen-Fu Chu, et al., "Comparison of p-Side Down and p-Side Up GaN Light-Emitting Diodes Fabricated by Laser Lift-Off", *Japan Journal of Applied Physics*, vol. 42, Part 2, No. 2B, pp. L147-L150, (Feb. 15, 2003).

W.H. Li, et al., "Electrochemical Deposition of Copper on Patterned Cu/Ta(N)SiO₂ Surfaces for Super Filling of Sub-Micron Features", *Journal of Applied Electrochemistry*, vol. 31, pp. 1395-1397, (Aug. 20, 2001).

Zhifang Fan, et al., "Very Low Resistance Multilayer Ohmic Contact to n-Gan," *Applied Physics Letters*, vol. 68, Issue 12, pp. 1672-1674, (Mar. 18, 1996).

I. Schnitzer, et al., "30% External Quantum Efficiency from Surface Textured, Thin-Film Light-Emitting Diodes," *Applied Physics Letters*, vol. 63, Issue 16, pp. 2174-2176, (Oct. 18, 1993).

Shyi-Ming Pan, et al., "Improvement of InGa_N-Ga_N Light-Emitting Diodes with Surface-Textured Indium-Tin-Oxide Transparent Ohmic Contacts," *IEEE Photonics Technology Letters*, vol. 15, Issue 5, pp. 649-651, (May 2003).

Chul Huh, et al., "Improved Light-Output and Electrical Performance of InGa_N-Based Light-Emitting Diode by Microroughening of the p-GaN Surface," *Journal of Applied Physics*, vol. 93, Issue 11, pp. 9383-9385, (Jun. 1, 2003).

F.A. Kish, et al., "Very High-Efficiency Semiconductor Wafer-Bonded Transparent-Substrate (Al_xGa_{1-x})_{0.5}In_{0.5}P/GaP Light-Emitting Diodes," *Applied Physics Letters*, vol. 64, Issue 21, pp. 2839-2841, (May 23, 1994).

R.H. Horng, et al., "AlGaInP Light-Emitting Diodes with Mirror Substrates Fabricated by Wafer Bonding," *Applied Physics Letters*, vol. 75, Issue 20, pp. 3054-3056, (Nov. 15, 1999).

H. Sugawara, et al., "Characteristics of a Distributed Bragg Reflector for the Visible-Light Spectral Region using InGaAlP and GaAs: Comparison of Transparent- and Loss-Type Structures," *Journal of Applied Physics*, vol. 74, Issue 5, pp. 3189-3193, (Sep. 1, 1993).

PCT International Search Report for PCT Application No. PCT/SG2003/000222 containing Communication relating to the Results of the Partial International Search Report, 3 pgs., (Dec. 9, 2003).

PCT International Search Report for PCT Application No. PCT/SG2003/000223 containing Communication relating to the Results of the Partial International Search Report, 3 pgs., (Dec. 9, 2003).

PCT International Search Report for PCT Application No. PCT/SG2005/000061 containing Communication relating to the Results of the Partial International Search Report, 2 pgs., (May 12, 2005).

PCT International Search Report for PCT Application No. PCT/SG2005/000062 containing Communication relating to the Results of the Partial International Search Report, 2 pgs., (May 12, 2005).

PCT International Search Report for PCT Application No. PCT/SG2006/000254 containing Communication relating to the Results of the Partial International Search Report, 4 pgs., (Nov. 16, 2006).

PCT International Search Report for PCT Application No. PCT/SG2006/000255 containing Communication relating to the Results of the Partial International Search Report, 3 pgs., (Nov. 6, 2006).

PCT International Search Report for PCT Application No. PCT/SG2006/000395 containing Communication relating to the Results of the Partial International Search Report, 3 pgs., (Feb. 26, 2007).

PCT International Search Report for PCT Counterpart Application No. PCT/SG2005/000261 containing Communication relating to the Results of the Partial International Search Report, 3 pgs., (Oct. 12, 2007).

PCT International Search Report for PCT Application No. PCT/SG2007/000288 containing Communication relating to the Results of the Partial International Search Report, 3 pgs., (Nov. 9, 2007).

PCT International Preliminary Report on Patentability for PCT Counterpart Application No. PCT/SG2007/000261, 9 pgs., (Mar. 17, 2008).

PCT Written Opinion of the International Searching Authority for PCT Counterpart Application No. PCT/SG2007/000261, 6 pgs., (Oct. 12, 2007).

Supplementary European Search Report for European Application No. 05711220.3-2222, 3 pgs., (Nov. 30, 2010).

Supplementary European Search Report for European Application No. 06784267.4-1235, 4 pgs., (Feb. 4, 2011).

Supplementary European Search Report for European Application No. 03818739, 1 pg., (Jan. 19, 2011).

Written Opinion for Chinese Patent Application No. 3827175.3, 6 pgs., (May 23, 2011).

* cited by examiner




FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6




FIG. 7




FIG. 8




FIG. 9




FIG. 10




FIG. 11




FIG. 12

EXTERNAL LIGHT EFFICIENCY OF LIGHT EMITTING DIODES

CROSS REFERENCE TO RELATED APPLICATIONS

This patent application is a U.S. National Phase application under 35 U.S.C. §371 of International Application No. PCT/SG2007/000261, filed on Aug. 16, 2007, entitled IMPROVEMENTS IN EXTERNAL LIGHT EFFICIENCY OF LIGHT EMITTING DIODES, which claims priority to Singapore patent application number 200605500-8, filed Aug. 16, 2006.

FIELD OF THE INVENTION

This invention relates to improvements in external light efficiency of light emitting diodes and refers particularly, though not exclusively, to light emitting diodes with surface texturing, include micro-lenses and/or surface roughening, on a light output surface, and a method of such surface texturing on a light output surface of light emitting diodes.

BACKGROUND OF THE INVENTION

Ga—N-based light emitting diodes (LEDs) have been intensively studied and developed in recent years. High efficiency, high power, GaN-based LEDs have attracted interest for applications such as displays, traffic signals, back lighting for mobile/cellular telephones and similar apparatus, and white light sources. Reducing cost and improving light output efficiency are important factors to enable such GaN LEDs to succeed in the mainstream lighting market.

In general, the internal quantum efficiency (η_i) for GaN-based LEDs is significantly less than 100% due to crystal quality and epitaxial layer structure. A typical (η_i) can reach about 70 to 80%. Further improvement has proven difficult to achieve. The external quantum efficiency (η_{ext}) is still much lower than internal quantum efficiency. This is because the light extraction efficiency of conventional GaN-based LEDs is limited by total internal light reflection, which occurs at the semiconductor-air interface due to the high refractive index of GaN ($n \approx 12.5$) compared to air ($n=1$). The critical angle for the light generated in the active region is only about 23° . Most of the light generated is repeatedly reflected into the substrate and eventually absorbed. Assuming that light emitted from sidewalls and the bottom is neglected, only a small fraction (4%) can be extracted from the surface.

Conventional GaN-based LEDs grown by metalorganic chemical vapor deposition (MOCVD) use a nonconductive sapphire substrate. The epitaxial layers on the sapphire substrate consists of usually a light-generating layer (active region) sandwiched between a relatively thick n-type doped GaN layer and relatively thin p-type doped GaN layer. The n-type GaN layer is formed by a stack of multiple layers (undoped or doped to n-type semiconductor made of GaN related materials like GaN, AlGaIn, or InGaIn, etc.) on the sapphire, while the p-type GaN layer is formed by a stack of multiple layers (undoped or doped to p-type semiconductor made of GaN related materials like GaN, AlGaIn, or InGaIn, etc.) away from the sapphire. The top p-GaN surface epitaxial layer is Ga-Polar which is often used as light extraction surface. The poor thermal conductivity of the sapphire substrate, and the relatively high current densities, combine to degrade the device performance due to excessive heating from the active layer during operation. At the same time, the relatively thin p-GaN layer (usually less than 0.5 micrometer) and the high resistivity of p-GaN, is highly

sensitive to plasma damaging and is difficult to use for dry surface texturing. Furthermore, Ga-polar GaN is chemically inert and is more difficult to wet etch than N-polar GaN. The other side of the active region, i.e., the n-GaN layer of the active region is usually much thicker (2 to 5 micrometers thick) than the p-type GaN layer, and is ideal for making surface texturing due to its thickness. However, this part is below the active region and on the sapphire. It is not able to be surface textured unless the sapphire is removed.

To address these problems, vertical laser liftoff of GaN LEDs and other methods have been developed to detach the sapphire from the GaN epitaxial films grown on it. Flip-chip or other bonding technologies have also been developed to attach the GaN films to a new substrate with good thermal conductivity. Different surface roughening techniques on exposed LED N-polar n-GaN surface have also been developed, including ICP plasma etching and wet etching.

The formation of micro-lenses on an output surface of a light emitting diode has been proposed. However, in the main it is not possible as the active region is close to the light emitting surface on the p-type GaN layer and the forming of the micro-lenses or surface roughing may damage the active region.

SUMMARY OF THE INVENTION

In accordance with a first preferred aspect there is provided a method to improve the external light efficiency of light emitting diodes, the method comprising etching an external surface of an n-type layer of the light emitting diode to form surface texturing, the surface texturing reducing internal light reflection to increase light output.

According to a second preferred aspect, there is provided a light emitting diode comprising an external surface of an n-type layer of the light emitting diode having surface texturing formed by etching, the surface texturing being for reducing internal light reflection for increasing light output and external light efficiency of the light emitting diode.

According to a third preferred aspect, there is provided a light emitting diode comprising an external surface of an n-type layer of the light emitting diode, and layer of another material being formed on an external surface of the n-type layer, an outermost layer of the layer of another material being surface textured for reducing internal light reflection for increasing light output and external light efficiency of the light emitting diode.

For all aspects the active layer may comprise of one or more of: a quantum well, quantum wells, quantum dots, and quantum wires. The surface texturing may be by wet etching with a chemical solution. The chemical solution may be an aqueous solution of potassium hydroxide at an elevated temperature for a predetermined period. Agitation of the light emitting diode may be used during the etching. The agitation may be by ultraviolet illumination. Additionally or alternatively, the surface texturing may be by dry etching. The dry etching may be plasma etching, plasma bombardment or laser processing. The dry etching may be before or after the wet etching.

The surface texturing may be at least one of: surface roughening, micro-lenses, and surface roughened micro-lenses, holes, voids, pillars and vias. The micro-lenses may be selected from: hemispherical, substantially hemispherical, hemispherical with a flat top, a segment of a sphere, pyramidal, cylindrical, and cuboid. The micro-lenses may be of:

- (a) a spacing between the micro-lenses in the range 2 to 3 μm ;
 (b) a pitch of substantially 6 μm ; and
 (c) a radius of substantially 2 μm .

The micro-lenses may be substantially pyramidal and may have facets at an angle of substantially 58°. The surface texturing may be over a part of the external surface. The surface texturing may be in light spaces formed between joining portions and an outer portion of a current dissipation array on the external surface.

A first ohmic contact may be formed on the external surface of the n-type layer and a second ohmic contact may be formed on p-type layer external surface. The second ohmic contact may reflect light for enhancing light emission of the light emitting diode. The second ohmic contact may comprise a stack of multiple layers of metals and their alloys. The metal may be silver, aluminum or another highly reflective metal. The highly reflective metal may be for a light reflection layer for enhancing light reflection of the light emitting diode. The second ohmic contact may cover the entire p-type layer external surface. Alternatively, the second ohmic contact may cover a portion of the p-type layer external surface, with the remainder of the p-type layer external surface being at least partially covered with at least one reflective material for reflecting light for enhancing light emission of the light emitting diode.

The p-type layer, the active layer and the n-type layer may be of one or more of a GaN-related material such as, for example, GaN, InGaN, AlGaIn, AlGaInN, InN and AlN.

Surface texturing may also be on the p-type side by surface texturing at least one layer selected from: the p-type layer, the ohmic contact layer, and the contact layer.

BRIEF DESCRIPTION OF THE DRAWINGS

In order that the present invention may be fully understood and readily put into practical effect, there shall now be described by way of non-limitative example only preferred embodiments of the present invention, the description being with reference to the accompanying illustrative drawings.

In the drawings:

FIG. 1 is a vertical cross-sectional view of a first preferred embodiment;

FIG. 2 is an enlarged view of a part of FIG. 1;

FIG. 3 is an enlarged view of the right-hand end of FIG. 2;

FIG. 4 is a top plan view of the embodiment of FIG. 1;

FIG. 5 is a photomicrograph of a portion of a light emitting device according to the first preferred embodiment;

FIG. 6 is a scanning electron microscope image of a second preferred embodiment;

FIG. 7 is a more detailed image of a portion of FIG. 6;

FIG. 8 is a graph of L-I characteristics for different etching times;

FIG. 9 is a graph of I-V characteristics for different etching times;

FIG. 10 is an enlarged side view of a third preferred embodiment;

FIG. 11 is an enlarged side view of a fourth preferred embodiment; and

FIG. 12 is an enlarged side view of a fifth preferred embodiment.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

To refer to FIGS. 1 to 4 there is shown a first preferred embodiment being a light emitting diode 100 having:

- a first contact layer 101 of conductive metal;
 a seeding layer 102, a reflective layer 103;
 an ohmic contact layer 104;
 a p-type material layer 105 such as, for example, GaN;
 a plurality of epitaxial layers forming an active layer 106;
 and
 a conductive layer 107 of n-type material such as, for example, GaN.

Any layer may be a stack of multiple layers. The n-type layer 107 is relatively thick, whereas the p-type layer 105 is relatively thin. The active layer 106 may be one or more of: a quantum well, quantum wells, quantum dots and quantum wires.

The conductive layer 107 is for the transmission of light generated in the active layer 106, the light passing through an external light output surface 108 of conductive layer 107. The external surface 108 is the external surface of the air-n-GaN interface. A bonding pad 109 is formed on the external surface 108. A current dissipation array 110 may also be formed on the external surface 108.

The external surface is surface textured to improve external light efficiency by reducing total internal reflection. Surface texturing may be by one or more of surface roughening, micro-lenses, surface roughened micro-lenses, holes, voids, pillars, and vias. One way of surface texturing is to etch the external surface 108 to form a plurality of micro-lenses 111 from external surface 108. The micro-lenses 111 are preferably hemispherical or close to hemispherical. However, they may be of any other suitable shape such as, for example, hemispherical with a flat top, a segment of a sphere, pyramidal, cylindrical, cuboid, and so forth.

The micro-lenses 111 may be of any suitable size and spacing. For example, the spacing between the micro-lenses 111 may be of the order of 2 or 3 μm ; the pitch (the spacing between centres of adjacent micro-lenses 111) may be of the order of about 6 μm ; and each micro-lenses may have a radius of the order of about 2 μm .

As shown on FIGS. 2 and 3, arrows 211, 212 and 213 represent light generated in active layer 106 and passing through layer 107. The majority of the light will pass into micro-lenses 111 or will be incident upon the internal surface 114 of the air/GaN interface. When the angle of incidence of a light beam 211, 212, 213 contacting the internal surface 114 between micro-lenses 111, or the inner surface 113 of micro-lenses 111, at an angle 215 less than the critical angle the light will pass through inner surface 113 and internal surface 114 and will thus be output from the LED 100. If the angle 215 is greater than the critical angle, the light will be reflected by inner surface 113 and internal surface 114. The angle 215 is the angle between the incident light beam 214 and a line 516 perpendicular to a tangent 517 at the point where beam 214 is incident upon surface 113, 114. The critical angle is when angle 215 is such that light beam 214 is reflected by inner surface 113 or internal surface 114 rather than passing through inner surface 113 or internal surface 114 respectively. The critical angle will depend on the material of n-GaN layer 107 and the wavelength of the light 214. If the angle 215 is 0°, the beam 214 will pass through inner surface 113 or internal surface 114 unaffected. If the angle 215 is between the critical angle and 0°, the beam 214 will pass through inner surface 113 or internal surface 114 but may be refracted. A likely range for the angle 215 is 20 to 35°. As noted earlier, for most n-GaN materials and LEDs, the critical angle is about 23°.

Therefore, by controlling the material, size, shape and spacing of micro-lenses 111 it is possible to control the direc-

tion and extent of light output from the light emitting diode **100**. This may be to the extent that LED **100** could output a focused beam of light.

FIGS. **4** and **11** show the arrangements of the microlenses **111** in a current dissipation array **109**, **110** on the external surface **108**. The nature, purpose and construction of array **109,110** is fully disclosed in co-pending Singapore, patent application number 200606050-3 dated Sep. 4, 2006 entitled "Electrical Current Distribution in Light Emitting Devices" and granted as SG 140512; the contents of which are incorporated herein by reference as if disclosed herein in its entirety.

The array **109**, **110** comprises an outer portion **110** connected to the bonding pad **109** by joining portions **115**. Between joining portions **115** and outer portion **110** are a number of light spaces **421**, **422**, **423** and **424** in which the micro-lenses **111** are located. The light spaces **421**, **422**, **423** and **424** may each be of substantially the same size and shape, or may different. The number of micro-lenses **111** in each light space **421**, **422**, **423** and **424**, and how they are arrayed, may be the same, or may differ from one light space to the next. A reflective layer **116** may be formed under or within array **109**, **110**.

The microlens can be formed by etching part of the semiconductor LED. First, photoresist is spun onto the surface, and then patterns are formed on the resist by standard photolithography. These photoresist patterns act as subsequent etching mask for microlens formation. Instead of the photoresist, other materials can also be used as an etching mask. After etching and removal of any residual photoresist, the microlens is formed.

In a second embodiment the surface texturing is surface roughening formed by crystallographic wet etching of all or part of external surface **108**. This is by subjecting the n-GaN surface **108** to aqueous potassium hydroxide etching at a temperature such as, for example, room temperature to 200 C for a predetermined period. The period may be as small as a few seconds up to several hours. For example, the temperature may be 90° C. and the predetermined period may be 7 minutes. The aqueous potassium hydroxide solution may be a 2 Mole potassium hydroxide solution, but other concentrations may be used. FIG. **6** shows that the surface **108** is roughened with small grains and FIG. **7** shows that the surface morphology of the n-GaN surface **108** displays a high level of roughness at the sub-micron scale with a dense, hexagonal pyramid structure being formed. The facets of the pyramids are in planes inclined at about 58° 4°.

Agitation of the light emitting diode may be used during the etching. The agitation may be by ultraviolet illumination. Additionally or alternatively, the surface texturing may be by dry etching. The dry etching may be plasma etching, plasma bombardment or laser processing. The dry etching may be before or after the wet etching.

Such dense nanotip pyramidal structures can be used as nanolenses to increase the light extraction efficiency of GaN-based LEDs. As shown in FIG. **7**, some of the large pyramids were broken and new small pyramids tips were formed on the top of them. The new, small pyramids grow with time. In such way, the etching of the n-GaN surfaced **108** can continue.

FIG. **8** shows the electrical luminescence ("EL") output power from surface **108** versus the injection current (I-I) with different etching times. The data was obtained from the same LED dies before and after KOH wet etching and measured on the wafer before dicing, so that any factor other than the surface morphology could be neglected. The output power at a given current increased significantly after surface roughen-

ing. After 7 minutes of KOH etching, the light output power increased by a factor of 2.5 to 3.

FIG. **9** shows a comparison of the measured I-V characteristic before and after KOH etching. The degradation of forward voltage drop (V_f) after KOH etching is mainly due to N-metal deterioration. The aluminum inside the Ti/Al/Ti/Au N-metal will slowly deteriorate during KOH etching. This problem may be solved by depositing N-metal after surface roughening. The reverse leakage current does not degrade with the increase of etching time.

FIG. **10** shows a third preferred embodiment which is a combination of surface roughening **1001** on the outside surface **112** of micro lenses **111**. The surface roughening **1001** may be over all or part of surface **108** and/or all or part of micro lenses **111**. In this way the n-GaN surface **108** may have an untreated surface and/or a surface roughened **1001** surface and/or micro lenses **111** and/or micro lenses **111** with surface roughening **1001**.

As shown in FIG. **12**, a layer **1130** of another material may be formed on the external surface **108** of the n-type layer. This may be before or after the surface is surface textured. An outermost surface **1131** of the layer of another material is surface textured for reducing internal light reflection for increasing light output and external light efficiency of the light emitting diode. Surface texturing may be as described above.

The ohmic contact layer **104** is formed on the external surface of the p-type layer **105**. The ohmic contact **104** may reflect light for enhancing light emission of the light emitting diode. The ohmic contact layer **104** may comprise a stack of multiple layers of metals and their alloys. The metal may be silver, aluminum or another highly reflective metal. The highly reflective metal may be for a light reflection layer for enhancing light reflection of the light emitting diode. The second ohmic contact layer **104** may cover the entire external surface of the p-type **105**. Alternatively, the ohmic contact layer **104** may cover a portion of the external surface of the p-type layer **105**, with the remainder of the external surface of the p-type layer **105** being at least partially covered with at least one reflective material for reflecting light for enhancing light emission of the light emitting diode.

The p-type layer **105**, the active layer **106** and the n-type layer **107** may be of one or more of a GaN-related material such as, for example, GaN, InGaN, AlGaIn, AlGaInN, InN and AlN.

In addition to the surface texturing on the n-type layer **107**, surface texturing may be performed on the p-type side. This may be on p-type layer **105** and/or contact layer **101** and/or ohmic contact layer **104**.

Whilst there has been described in the foregoing description preferred embodiments of the present invention, it will be understood by those skilled in the technology concerned that many variations or modifications in details of design or construction may be made without departing from the present invention.

What is claimed is:

1. A method to improve the external light efficiency of a light emitting diode, the light emitting diode including an n-type layer, a p-type layer, an ohmic contact layer, and a contact layer, the method comprising:

etching an external surface of the n-type layer to form surface texturing, the surface texturing reducing internal light reflection to increase light output,

wherein the surface texturing is at least one selected from the group consisting of: micro-lenses and surface roughened micro-lenses, and

wherein the surface texturing is over a part of the external surface of the n-type layer and is in light spaces formed between joining portions and an outer portion of a current dissipation array on the external surface of the n-type layer.

2. The method as claimed in claim 1, wherein the light emitting diode has an active layer between the n-type layer and the p-type layer and the active layer comprises at least one selected from the group consisting of: a quantum well, quantum wells, quantum dots, and quantum wires.

3. The method as claimed in claim 1, wherein the surface texturing is formed by wet etching with an aqueous solution of potassium hydroxide at a temperature for a predetermined period.

4. The method as claimed in claim 1, further comprising: agitating the light emitting diode with ultraviolet illumination during the etching.

5. The method as claimed in claim 1, wherein the etching is dry etching, the dry etching being at least one selected from the group consisting of: plasma etching, plasma bombardment, or laser processing; and the dry etching being performed before or after wet etching.

6. The method as claimed in claim 1, wherein the micro-lenses are selected from the group consisting of: hemispherical, substantially hemispherical, hemispherical with a flat top, a segment of a sphere, pyramidal, cylindrical, and cuboid; and the micro-lenses are of:

- (a) a spacing between the micro-lenses in the range 2 to 3 μm ;
- (b) a pitch of substantially 6 μm ; and
- (c) a radius of substantially 2 μm .

7. The method as claimed in claim 2, wherein a first ohmic contact is formed on the external surface of the n-type layer and a second ohmic contact is formed on a surface of the p-type layer, the second ohmic contact configured to reflect light to enhance light emission of the light emitting diode and comprising a stack of multiple layers of metals and their alloys, at least one of the metals being a highly reflective metal including at least one of: silver and aluminum, the highly reflective metal serving as a light reflection layer to enhance light reflection of the light emitting diode.

8. The method as claimed in claim 7, wherein the second ohmic contact covers the surface of the p-type layer entirely.

9. The method as claimed in claim 7, wherein the second ohmic contact covers a portion of the surface of the p-type layer, with the remainder of the surface of the p-type layer being at least partially covered with at least one reflective material, the at least one reflective material reflecting light to enhance light emission of the light emitting diode.

10. The method as claimed in claim 2, wherein the p-type layer, the active layer, and the n-type layer are at least one selected from the group consisting of: a GaN-related material, GaN, InGaN, AlGaInN, InN and AlN.

11. The method as claimed in claim 1 further comprising: forming surface texturing on at least one layer selected from the group consisting of: the p-type layer, the ohmic contact layer, and the contact layer.

12. A light emitting diode comprising:

an n-type layer having surface texturing over a part of an external surface of the n-type layer to reduce internal light reflection and increasing light output and external light efficiency of the light emitting diode,

wherein the surface texturing is formed by etching and is at least one selected from the group consisting of: micro-lenses and surface roughened micro-lenses, and wherein the surface texturing is in light spaces formed between joining portions and an outer portion of a current dissipation array on the external surface of the n-type layer.

13. The light emitting diode as claimed in claim 12, further comprising:

a p-type layer; and

an active layer between the n-type layer and the p-type layer, the active layer comprising at least one selected from the group consisting of: a quantum well, quantum wells, quantum dots, and quantum wires.

14. The light emitting diode as claimed in claim 12, wherein the micro-lenses are selected from the group consisting of: hemispherical, substantially hemispherical, hemispherical with a flat top, a segment of a sphere, pyramidal, cylindrical, and cuboid; and the micro-lenses are of:

- (a) a spacing between the micro-lenses in the range 2 to 3 μm ;
- (b) a pitch of substantially 6 μm ; and
- (c) a radius of substantially 2 μm .

15. The light emitting diode as claimed in claim 13, wherein a first ohmic contact is formed on the external surface of the n-type layer and a second ohmic contact is formed on a surface of the p-type layer, the second ohmic contact configured to reflect light to enhance light emission of the light emitting diode and comprising a stack of multiple layers of metals and their alloys, at least one of the metals being a highly reflective metal including at least one of: silver and aluminum; the highly reflective metal serving as a light reflection layer to enhance light reflection of the light emitting diode.

16. The light emitting diode as claimed in claim 15, wherein the second ohmic contact covers the surface of the p-type layer entirely.

17. The light emitting diode as claimed in claim 15, wherein the second ohmic contact covers a portion of the surface of the p-type layer, with the remainder of the surface of the p-type layer being at least partially covered with at least one reflective material, the at least one reflective material reflecting light to enhance light emission of the light emitting diode.

18. The light emitting diode as claimed in claim 13, wherein the p-type layer, the active layer, and the n-type layer are at least one selected from the group consisting of: a GaN-related material, GaN, InGaN, AlGaInN, InN and AlN.

19. The light emitting diode as claimed in claim 13, further comprising:

surface texturing on at least one layer selected from the group consisting of: the p-type layer, the ohmic contact layer, and the contact layer.

* * * * *